

# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN

### Product Information

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and specialty grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

**Delrin® 525GR is a 25% glass-reinforced acetal homopolymer for injection molding. It has very high strength, stiffness, and high deflection temperature, excellent creep resistance, and good notched impact properties.**

General information	Value	Unit	Test Standard
Resin Identification	POM-GF25	-	ISO 1043
Part Marking Code	POM-GF25	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate	5	cm <sup>3</sup> /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	9500	MPa	ISO 527-1/-2
Stress at break	160	MPa	ISO 527-1/-2
Strain at break	3	%	ISO 527-1/-2
Flexural Modulus	9150	MPa	ISO 178
Flexural Strength	245 <sup>[1]</sup>	MPa	ISO 178
Tensile creep modulus			ISO 899-1
1h	8500	MPa	
1000h	6000	MPa	
Charpy impact strength			ISO 179/1eU
73 °F	60	kJ/m <sup>2</sup>	
-22 °F	50	kJ/m <sup>2</sup>	
Charpy notched impact strength			ISO 179/1eA
73 °F	10	kJ/m <sup>2</sup>	
-22 °F	10	kJ/m <sup>2</sup>	
Hardness, Rockwell, M-scale	101	-	ISO 2039-2
Hardness, Rockwell, R-scale	122	-	ISO 2039-2
1: Strain at break = 3.2%			
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18 °F/min	178	°C	ISO 11357-1/-3
Temp. of deflection under load			ISO 75-1/-2
260 psi	172	°C	
65 psi	176	°C	
Coeff. of linear therm. expansion, parallel	35	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	100	E-6/K	ISO 11359-1/-2
RTI, electrical			UL 746B
30mil	50	°C	
60mil	50	°C	
120mil	50	°C	
RTI, impact			UL 746B
30mil	50	°C	
60mil	50	°C	
120mil	50	°C	

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com



# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN

		UL 746B	
RTI, strength			
30mil	50	°C	
60mil	50	°C	
120mil	50	°C	
Flammability		Value	Unit
Burning Behav. at 60mil nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.75	mm	IEC 60695-11-10
UL recognition	yes	-	UL 94
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	49	mm/min	ISO 3795 (FMVSS 302)
Electrical properties		Value	Unit
Relative permittivity			IEC 62631-2-1
100Hz	3.7	-	
1MHz	3.8	-	
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Other properties		Value	Unit
Humidity absorption, 80mil	0.17	%	Sim. to ISO 62
Water absorption, 80mil	1.26	%	Sim. to ISO 62
Density	1590	kg/m <sup>3</sup>	ISO 1183
VDA Properties		Value	Unit
Emissions	<8	mg/kg	VDA 275
Fogging, G-value (condensate)	1.2	mg	ISO 6452
Injection		Value	Unit
Drying Recommended	yes	-	-
Drying Temperature	≥80	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.2	%	-
Melt Temperature Optimum	215	°C	-
Min. melt temperature	210	°C	-
Max. melt temperature	220	°C	-
Mold Temperature Optimum	90	°C	-
Min. mold temperature	80	°C	-
Max. mold temperature	100	°C	-
Hold pressure range	80 - 100	MPa	-
Hold pressure time	8	s/mm	-
Annealing time, optional	30	min/mm	-
Annealing temperature	160	°C	-

### Characteristics

Processing	• Injection Molding
Delivery form	• Pellets
Additives	• Release agent
Regional Availability	• North America • Europe • Asia Pacific • South and Central America • Near East/Africa • Global

### Processing Texts

#### Injection molding

Drying is recommended, but not necessary for newly opened packaging stored in a dry location.

Follow the drying guidelines above in the following cases:

- If moisture is above the Processing Moisture Content recommendation,
- When a resin container is damaged,
- When the material is not properly stored in a dry place at room temperature, or

Revised: 2017-10-27

Page: 2 of 7

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN

· When packaging stays open for a significant time.

Revised: 2017-10-27

Page: 3 of 7

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

#### Asia Pacific

TEL: +86 0769-82339888 / 87798999

#### Europe/Middle East/Africa




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

# DuPont™ Delrin® 525GR NC000


## ACETAL RESIN

### Diagrams

#### Viscosity-shear rate




#### Shearstress-shear rate



# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN


Stress-strain



# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN

Secant modulus-strain



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Delrin® 525GR NC000

## ACETAL RESIN

### Specific volume-temperature (pvT)



Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

#### Asia Pacific

TEL: +86 0769-82339888 / 87798999

#### Europe/Middle East/Africa

